

### 802

### High Vacuum Grease

Excellent Thermal Stability, Electrically and Thermally Insulating

TYPICAL PROPERTIES	
Product	802
Appearance	Paste
Color	Translucent
Penetration	185
Specific Gravity	1.04
Drop Point, °C	>300
Evaporation, 24hr, 200°C, %	1.1
Bleed, 24hr, 200°C, %	0.05
Service Temperature, °C	-40 to 204

#### General Information

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

#### Storage and Shelf Life

Store product in a cool, dark place when not in use. This product has a one year minimum shelf life after date of manufacture, unless otherwise specified, when stored at 60-80°F (16-27°C) in original, unopened containers.

#### Note

The data contained in this technical data sheet are furnished for information only. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein. INCURE will not be liable for any indirect, special, incidental or consequential loss or damage arising from this INCURE product, regardless of the legal theory asserted. INCURE recommends that each user adequately test its proposed use and application before repetitive use, using this data as a guide.